

AD-545 HS Acrylic Clear



Technical Data

| | |
|---------------------|-------------------|
| Color: | Clear |
| Mix Ratio: | 4:1 |
| Activator: | AD-546,547,548 |
| Weight Solids(RTS): | 43.3% |
| Film Build: | 1.0-1.8 mils |
| Coverage: | 694.5 sq. ft./gal |
| Dry Time: | 10-16 Hours |
| Pot Life: | 1 ½ -2 Hours |
| V.O.C. | 4.2 lbs/gal |

AD-545 is a high solids, excellent quality clearcoat formulated to meet 4.2 lb/gal VOC restrictions. #545 is designed for use in air dry, downdraft booths, and force dry booths. It exhibits excellent flow out and buffing characteristics thus providing an extremely high gloss and D.O.I.

Features:

- Easy Application
- Fast Dry
- Air Dry or Bake

Advantages:

- Less Buffing
- Same Day Delivery
- Versatile

Benefits:

- Increase Productivity
 - Reduces Delivery Time
 - Fits Most Shop Conditions
-

Special Instructions

1. Apply 1 medium coat allowing a 10-15 minute flash time then follow with a full wet second coat
 2. Allow to dry 10-16 hours at 77°F or 40 minutes at 140°F with a 1 hour cool down before sanding or polishing
-

Compare To:

| | |
|-------------------|-------------------|
| Dupont® | 72200S™ Clearcoat |
| Sherwin Williams® | CC-637 Clearcoat |
| BASF® | DC-88 NR |
| Transtar® | 6841 |